

FILM-LAMINATION PRODUCT

SUSLITE

SUS-LOOK

DK DKDONGSHIN


SUSLITE

HOME APPLIANCE PRODUCT

ABOUT SUSLITE

This product replicates the depth and texture of stainless steel with a rich hairline finish through brushing (scratch) processing on the PET film surface. It delivers a natural and realistic metallic finish at a reasonable price while offering a luxurious appearance and a wide range of color options, making it a practical and high-quality alternative to real stainless steel.

STRUCTURE OF PRODUCT




APPLICATION



Refrigerator Door



Washing Machine



TV & Monitor Bezel

PRODUCT STANDARDS

Thickness	Width	Coil.I.D.
GI, EGI 0.3 - 1.0T	500 - 1,500mm	Discussion

PRODUCT PROPERTY

Property	Measurement	Test Standards
Bending(Adhesion)	25°C x 180° Bending	Customer Discussion
M.E.K Rubbing	M.E.K Rubbing x 1kg	30-50 ↑ (Flat)
Pencil Hardness	MIT-UN x 1kg x 45°	B ~ F ↑
Erichsen Test	5mm Cross cut x Erichsen 6mm	Natural Pelling Off
Impact Test	1/2" x 50cm x 500g	No Crack & No Peel off
Resistance of UV ravs	25°C x 15W x 20cm x 24hrs	DE ≤ 2.5
Chemical Resistance	25°C x 5% NaOH / HCL / CH3COOH x 24hrs	No Change Color&Surface
Anti-Solvent Test	25°C x Xylene/Toluene/Benzene x 24hrs	No Change Color&Surface
Salt Spray Test	35°C x 5% Nacl x SALT SPRAY (EG I : 240hrs , GI : 480hrs)	No more 2mm blister on the cross-cut

* The above criteria may vary depending on the application, material, color, and gloss, requiring prior consultation

SEOUL OFFICE

10F, 46, Dadong-gil, Jung-gu,
Seoul, Korea
Tel : 82-2-3475-1893 Fax : 82-2-549-8340

HEAD OFFICE & FACTORY

154, Daesong-ro, Nam-gu, Pohang-si,
Gyeongsangbuk-do, Korea
Tel : 82-54-280-0211 Fax : 82-54-286-0176